

Directions for use

- 1** Make sure that the substrate is free of dust, clean and dry. Never apply Bond or mastic to a painted surface. Bond is not compatible with QwikSet Mirro-Mastic® or SuperSet Mirro-Mastic®.

- 2** Brush or roll Bond on the substrate and allow to dry.

- 3** For very porous substrates, two coats of Bond may be necessary. Allow the first coat to dry before applying the second.

- 4** Drying time is approximately one hour, but will depend on temperature, humidity and type of substrate.

- 5** Allow drying time before applying mastic.

- 6** One gallon (3.785L) of Bond will cover approximately 400 square feet (37.16 square meters) of substrate.

- 7** Cleanup can be done with mineral spirits.

- 8** Do not thin bond.

- 9** For technical questions, contact Palmer Products at 800.431.6151 or palmer@mirro-mastic.com. The SDS and directions in French and Spanish are available at mirro-mastic.com.

NOTE: Palmer Products makes no warranties, express or implied, with respect to Mirro-Mastic® Bond or otherwise, and hereby disclaims any and all warranties, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. Palmer Products' sole liability and the customer's sole and exclusive remedy with respect to any claim arising out of or relating to either Mirro-Mastic® Bond or the use of Mirro-Mastic® Bond, shall be the replacement of the Mirro-Mastic® Bond. Palmer Products assumes no responsibility if the product is misused.